Product Data Sheet

No. 1188 - 02/17

MRO BRITE GALVANIZE COATING

AEROSOL CARB VOC <80% / MIR < 1.25

PRODUCT NUMBERS: 188 - 12 OZ. NET WT. AEROSOL

I. GENERAL DESCRIPTION

Description: Aervoe's MRO Brite Galvanize Coating is a cost effective way to repair hot-dip galvanizing that has been damaged by abrasion, scratching, cutting or welding. Cosmetically repairs both ferrous and nonferrous surfaces. Uses zinc metallic flake that is 97% pure. An exceptionally smooth-flowing product that leaves a bright metal coating with a reflective metallic sheen containing 65% zinc in the dry film. The Zinc fuses to metal substrates to provide protection similar to hot-dip galvanizing.

Benefits: Restores galvanized surfaces to the bright look of hot-dip. Stops rust and corrosion on any iron or steel surface. Even if the surface is scratched, the zinc surface will continue to protect against corrosion. Brite Galvanize offers the convenience of on-the-job application when hot-dip repair is necessary. Acceptable as a coating in federally inspected meat and poultry plants for application to structural surfaces where there is a possibility of incidental food contact. Does not contain lead, chromates, methylene chloride or fluorocarbons. Meets performance requirements of ASTM A780.

Application: Use on pipes, heavy equipment, highway guard rails, hand rails, welds, metal chain fences, bridges, storage tanks, corrugated metal buildings, transformers, television towers, signs and sign posts, railroad equipment, construction equipment and anywhere the bright look of hot-dipped surfaces is desired.

Directions: Whenever possible, repair should be applied within two hours of the damage to the galvanized surface; this prevents oxidation of the exposed areas. Surface should be free of dirt, dust, oil, grease, old paint, heavy mill scale, loose rust particles and any other contaminants that could prevent proper adhesion. Severely rusted areas should be cleaned with a wire brush to remove loose scale prior to application of MRO Brite Galvanize. For best results, repair material should extend at least three inches beyond edges of the damaged area to ensure continuity of galvanic action and used at temperatures between 60° and 80°F (16° to 27°C). Drying may be accelerated by applying heat. Align spray head with black mark on valve rim to insure complete evacuation of contents. Vigorously shake can for 2 minutes after hearing rattle of agitator ball (ball should release in 10 to 30 seconds), and intermittently (1 to 2 seconds) during use. Apply from a distance of 8 to 12 inches. Spray in light, sweeping strokes to avoid run and sags. Two light coats are better than one heavy coat. Whenever you must set the aerosol can aside for more than 2 minutes or are ready to store the can, then invert the can and spray for two seconds to clear dip tube, valve and tip to prevent zinc from drying in those areas.

Limitations: Please refer to the Safety Data Sheet for specific information on material hazards, etc. Do not apply at temperatures below 40°F (4°C), or if rain is imminent within 6 hours of application. Galvanizing products have a limited shelf life; use them within 12 months from the date of manufacture (guarantee is for 6 months from date of purchase and 12 months from date of manufacture).

Packaging:

Aerosol: Cans (211x604) Case (12/case): 12 net wt. (340 g) 13 lbs. (5.9 kg) 13.6 fl. oz. (402 ml) 0.47 CF (0.013 CM)











II. CHARACTERISTICS & PROPERTIES

Specifications: Aerosol complies	with CAR	B MIR regulation	ns
Appearance:			

Appearance.	A. 4. 11.
Class	Metallic
Coverage:	
Theoretical (at 1 mil dry)	
Practical (at 1/2 mil dry)	26sq. ft./can
Dry Schedule: (at 77° F [25° C], 50% Humidity at 1 mil, dry)	
To touch	
To handle	30 min
To recoat	After 24 hrs.
Full cure	24 hrs.
Performance and Chemical Properties:	
Weight per gallon	7.2 lbs/gal
Specific gravity	0.9
Flammability: Label marking	Extremely flammable
Flash point	<0°F (-18°C)
Operating temperature range	50° to 90°F (10° to 32°C)
Percent solids by weight	25%
Percent solids by volume	7%
Percent pigment by volume	2%
CARB VOC limit (metallic coatings)	<80%
CARB MIR limit (metallic coatings)	≤1.25
Interior durability	
Exterior durability	Excellent
Temperature resistance	150°F (65°C)
Color fastness	Excellent
Adhesion (ASTM D3359)	Excellent
Salt spray corrosion (ASTM B117)	
Paint thinner resistance	Excellent
Gasoline resistance	Poor
Motor oil resistance	Very Good
Pencil hardness (ASTM D3363)	<2B
Food contact rating	
Base Materials	. 6 ,
Resin system	Acrylic
Solvents (top two)	Acetone, n-Butyl Acetate
Propellant system	
	•

III. SHIPPING, STORAGE AND HEALTH

UN number	UN1950
Proper Shipping Description	Aerosols
Hazard Class	2.1
Packing Group	N/A
Limited Quantity	
Warehouse storage level number	NFPA 30B Level 2
Storage temperature	
Shelf life	
HMIS ratings	
Health	
Fire	
Reactivity	1

IV. MISCELLANEOUS

Contains no Ozone Depleting Substances (O.D.S.)

V. WARRANTY

1-year warranty to the original registered owner on all products from date of purchase. User returns, exchanges and defective refunds must be made with the original place of purchase. Because Aervoe cannot control Buyer's handling or use of product, Aervoe makes no warranty expressed or implied when not used or stored in accordance with directions. Aervoe shall not be liable for cost of labor, incidental or consequential damages, and this warranty is limited to replacement or repair of product or credit of purchase.